



W/R Sure Grip (PFGA) Black (196N1306)

PRODUCT DESCRIPTION

W/R Sure Grip (PFGA) was formulated using the latest waterborne technology that makes this product ideal for use over Galvanize and Aluminum substrates.

W/R Sure Grip (PFGA) provides excellent adhesion and a super hard finish almost immediately. Even though Sure Grip was formulated for Galvanize and Aluminum, it is also a great paint for Hot-Dipped or Cold Rolled Steel.

W/R SURE GRIP (PFGA) CAN BE USED FOR:

- Ornamental Iron
- Window Extrusions
- Industrial Equipment
- Patio Furniture
- Sheet Metal
- Plus, Many Other Uses

MIXING & APPLICATION

- Stir thoroughly prior to use.
- Conventional, airless or HVLP spray systems
- Brush for touch-up only
- When painting over new galvanized metal that is very shiny in appearance, it will be important to test for adhesion. This can be done by applying a small amount of paint on the surface and allowing it to dry for approximately 72 hours. Next, make a cross (X) cut in the paint film and apply tape over the cut. Press down firmly to assure that tape adheres to the paint and then, in one swift motion, pull the tape from the paint. If adhesion is poor, most of the paint between the cuts will be removed. If this happens, consult the manufacturer for further instructions.

THINNING: Water

CLEAN UP: Warm water

ORDERING: Available in single gallons.

TECHNICAL INFORMATION

SURFACE PREPARATION: Surface must be clean, dry, and free of dirt, grease, oil, loose rust, loose mill scale, and contaminants.

Recommended removal is SSPC-SP-3 Power Tool Cleaning, which can aid in assuring optimum adhesion.

PHYSICAL PROPERTIES

Type	Water Reducible
Components	One
Colors	Black
Volume Solids	35% ± 2%
Gloss	15% - 25%
Coverage	560 sq ft/gal @ 1 mil 224 - 372 sq ft/gal @ recommended dft
Recommended DFT	1.5 – 2.5 mils dry film
VOC	Theoretical unreduced 1.2 lb/gal
Dry to Touch	15 - 25 minutes @ 77° F
Dry Tack Free	35 - 45 minutes @ 77° F
Dry Hard	16 hours @ 77° F
Flash Point	N/A
Temperature Resistance	250° F Maximum
Pot Life	N/A
Shelf Life	6 months

02/17

The technical data furnished are true and accurate to the best of our knowledge at the date of issuance. It is subject to change without prior notice. It is suggested the user verify with Sumter Coatings, Inc. prior to specifying or ordering. Test results are believed to be reliable; however, no guarantee of accuracy is given or implied. We guarantee all products to conform to Sumter Coatings, Inc.'s quality control standards. Liability, if any, is limited to replacement of product. No other warranty or guarantee of any kind, expressed or implied, is made by Sumter Coatings, Inc., including fitness for a particular purpose.