

SUMTER COATINGS

HIGH PERFORMANCE PROTECTIVE COATINGS

EXPOSURE Light Industrial, Public Buildings	TYPICAL APPLICATIONS Warehouses, Manufacturing Plants, Schools, Storage Tank Exteriors	TYPE SYSTEM Alkyd Primer and Alkyd Topcoat	ALCOHOLS	ALIPHATIC HYDROCARBONS	ALKALI SOLUTIONS	ROCARBONS	ITER	KETONES	(O	MINERAL OILS	ORGANIC ACIDS	OXIDIZING AGENTS	SALT SOLUTIONS	ATER	ING	PRIMER	INTERMEDIATE	FINISH
	Manufacturing Plants, Schools, Storage Tank Exteriors	and Alkyd Topcoat									Ö	ŏ	SALTS	WASTE WATER	WEATHERING			
			\Diamond	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦	G	Heavy Duty Primer 100R9913 100D9914 2.0 mils DFT	High Performance Enamel 484 Line 1.5 Mils DFT	High Performance Enamel 484 Line 1.5 Mils DFT
Heavy Industrial	Plywood Plants, Sawmills	High Build Epoxy Primer Polyamide Cured and Urethane Topcoat	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦		E	Enviro-Pox 949 Line Epoxy Mastic High Build 3.0 mils DFT	None	Enviro-Tuff* 459 Line Urethane 2.0 mils DFT
Mild Chemical Exposure	Industrial Plants, Pulp and Paper Mills Cogeneration	Epoxy Mastic, High Build Polyamide Cured		♦	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦	F	Enviro-Pox 949 Line Epoxy Mastic High Build 5.0 mils DFT	None	Enviro-Pox 949 Line Epoxy Mastic High Build 5.0 mils DFT
Moderate Chemical, High Humidity Condensation	Natatoriums, Coastal Environments	Organic Zinc Rich Epoxy Primer and Urethane Topcoat	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦		E	Enviro-Zinc 100S9785 Organic Zinc Rich 3.0 mils DFT	None	Enviro-Tuff® 359 Line Urethane 5.0 mils DFT
Cayora Chaminal	Pulp and Paper Mills, Coal Handling, Chemical Plants, Sour Crude Refineries	Epoxy Mastic, High Build Polyamide Cured and Urethane Topcoat	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦	\Q	E	Enviro-Pox 949 Line Epoxy Mastic High Build 5.0 mils DFT	Enviro-Pox 949 Line Epoxy Mastic High Build 5.0 mils DFT	Enviro-Tuff® 459 Line Urethane 2.0 mils DFT
	Pulp and Paper Mills, Coal Handling Facilities, Dockside Exposures	Organic Zinc Rich Epoxy Primer and Epoxy Mastic High Build Polyamide Cured Topcoats	♦	♦	♦	♦	♦	♦	♦	♦	\Q	♦	\Q	\Q	F	Enviro-Zinc 100S9785 Organic Zinc Rich 3.0 mils DFT	Enviro-Pox 949 Line Epoxy Mastic High Build 5.0 mils DFT	Enviro-Pox 949 Line Epoxy Mastic High Build 5.0 mils DFT
Severe Chemical-	Capital structures where color and gloss retention are needed	Organic Zinc Rich Epoxy Primer, Epoxy Mastic High Build Polyamide Cured & Urethane Topcoat	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦		E	Enviro-Zinc 100S9785 Organic Zinc Rich 3.0 mils DFT	Enviro-Pox 949 Line Epoxy Mastic High Build 5.0 mils DFT	Enviro-Tuff* 359 Line Urethane 5.0 mils DFT
	New Construction, Pulp and Paper Mills, Power Plants, Coal Liquification, Cogeneration	Inorganic Zinc Rich Primer and Epoxy Mastic High Build Polyamide Cured Topcoats		♦	\$	♦	♦	♦	♦	♦	♦	♦	♦	♦	F	Enviro-Zinc 100S9715 Inorganic Zinc Rich 2.5 - 3.0 mils DFT	Enviro-Pox 949 Line Epoxy Mastic High Build 5.0 mils DFT	Enviro-Pox 949 Line Epoxy Mastic High Build 5.0 mils DFT
Severe Chemical	Where gloss and color retention are important	Inorganic Zinc Rich Primer and Epoxy Mastic High Build and Urethane Topcoat		♦	♦	♦	♦	♦	♦	♦	♦	♦	♦		E	Enviro-Zinc 100S9715 Inorganic Zinc Rich 2.5 - 3.0 mils DFT	Enviro-Pox 949 Line Epoxy Mastic High Build 5.0 mils DFT	Enviro-Tuff* 459 Line Urethane 5.0 mils DFT
Immersion, Severe Exposures	Waste Treatment Plants, Pulp and Paper Mills, Cogeneration Power Plants	Coal Tar Epoxy Polyamide Cured	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦		F	Coal Tar Epoxy 100N7728 8.0 mils DFT	None	Coal Tar Epoxy 100N7728 8.0 mils DFT

